

Zytel® 444AHS BK152

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 444AHS is a toughened, heat stabilised, black polyamide 66 resin for injection moulding. It is a high flow, processing friendly material.

Product information

Resin Identification	PA66-I	ISO 1043
Part Marking Code	>PA66-I<	ISO 11469
ISO designation	ISO 16396-PA66-I,,M1CG1H,S14-020	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	1.4 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	2400 / 1100	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	62 / 40	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	5.5 / 15	%	ISO 527-1/-2
Nominal strain at break	25 / >50	%	ISO 527-1/-2
Flexural modulus	2270 / -	MPa	ISO 178
Izod notched impact strength, 23°C	16 / -	kJ/m²	ISO 180/1A
Izod notched impact strength, -40°C	10.0 / -	kJ/m²	ISO 180/1A

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	65 / *	°C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	90 / *	E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	100 / *	E-6/K	ISO 11359-1/-2

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Zytel® 444AHS BK152

NYLON RESIN

Physical/Other properties

	dry/cond.		
Water absorption, 2mm	1.3 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	1.3 / *	%	Sim. to ISO 62
Density	1110 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Max. screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	50 °C
Max. mould temperature	90 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	4 s/mm
Hold Pressure Time (h is the max. wall thickness of the part in mm)	h^2+2 s
Ejection temperature	190 °C

Automotive

OEM	STANDARD
Ford	WSS-M4D706-B1
General Motors	Black, Part Specific Approval, Please Contact Your CE Representative For More Details.


Characteristics

Processing	Injection Molding
Special characteristics	Heat stabilised or stable to heat

Zytel® 444AHS BK152

NYLON RESIN


Stress-strain (dry)



Zytel® 444AHS BK152

NYLON RESIN


Stress-strain (cond.)



Zytel® 444AHS BK152

NYLON RESIN


Secant modulus-strain (dry)



Zytel® 444AHS BK152

NYLON RESIN


Secant modulus-strain (cond.)



Zytel® 444AHS BK152

NYLON RESIN


Tensile modulus-temperature (dry)



Zytel® 444AHS BK152

NYLON RESIN

Tensile modulus-temperature (cond.)



Printed: 2026-07-03

Page: 8 of 8

Revised: 2025-04-22 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

Copyright © 2026 Celanese or its affiliates. All rights reserved.

Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.