

Solumer™ 8705L

Polyolefin Elastomer

Introduction

Solumer™ 8705L is an **ethylene-octene copolymer** produced via Nexlene™ technology. It performs well in a wide range of general purpose thermoplastic elastomer applications and has excellent flow characteristics

Applications

- General purpose thermoplastic elastomers
- Wire and cable
- TPO(Thermoplastic olefins)
- Impact modification

Properties

		Typical Values	Unit	Test Method
Physical Properties	Density	0.868	g/cm ³	ASTM D792
	Melt index (2.16 kg @190°C)	0.5	g/10min	ASTM D1238
	Mooney viscosity (ML1+4 @ 121°C)	36	MU	ASTM D1646
Mechanical Properties¹	Tensile strength at break	105	kgf/cm ²	ASTM D638 ²
	Elongation at break	800	%	ASTM D638 ²
	Tensile modulus (100% Elongation)	32	kgf/cm ²	ASTM D638 ²
	Flexural modulus (1% secant)	155	kgf/cm ²	ASTM D790
	Tear strength (Type C)	46	kgf/cm ²	ASTM D624
	Hardness	Shore A (1 sec)	74	Hardness
		Shore D (1 sec)	23	ASTM D2240
Thermal Properties	Melting temperature	59	°C	SK Method
	Glass transition temperature	-54	°C	SK Method

¹ Evaluated using compression molded sample, process condition: 170 °C, 4 min

² Crosshead speed: 500 mm/min.

Notes

These are *typical values* and are *not to be construed as specifications*. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK geo centric Co.,LTD
51 Jong-ro, Jongno-gu,
Seoul, Republic of Korea
TEL +82-2-2121-7067

TS&D SK innovation Institute of Environmental Science & Technology,
325 Exporo, Yueseong-gu,
Daejeon, KOREA
TEL +82-42-609-8871