

Galden® HT80

perfluoropolyether

Galden® HT PFPE are inert, dielectric and high-performance heat transfer fluids with boiling points ranging from 55°C to 270°C. This range is broader than other fluorinated heat transfer fluids and enables PFPE to be used at end-use temperatures up to 290°C.

Syensqo offers a reliable and non-flammable Heat Transfer (HT) media for demanding applications, including:

- Semiconductor
- Chemical
- Pharmaceutical
- Vapor phase heating
- Transformer and super computer cooling
- Recirculating chillers
- Nuclear"

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Forms	• Liquid

Physical

	Typical Value	Unit
Density (25°C)	1.69	g/cm³
Average Molecular Weight	430	
Kinematic Viscosity	0.570	cSt
Solubility		
of air	26.0	ml gas/100 ml liquid
of water	< 10.0	wppm
Surface Tension (25°C)	16	dyne/cm
Vapor Pressure (25°C)	105	torr

Thermal

	Typical Value	Unit
Thermal Conductivity (25°C)	0.065	W/m/K
Boiling Point	80	°C
Heat of Vaporization - at Boiling Point	17.0	cal/g
Pour Point	-110	°C
Specific Heat Capacity (25°C)	0.23	cal/g/°C

Electrical

	Typical Value	Unit
Volume Resistivity (25°C)	1.0E+15	ohms-cm
Dielectric Constant (25°C)	1.89	
Dielectric Strength - 2.54 mm gap (25°C)	40	kV
Dissipation Factor - 1 KHz	2.0E-4	

Optical

	Typical Value	Unit	Test method
Refractive Index	1.28		ASTM D542

Galden® HT80

perfluoropolyether

Additional Information

Coefficient of thermal expansion: $0.0011 \text{ cm}^3/\text{cm}^3\text{°C}$

Notes

Typical properties: these are not to be construed as specifications.

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2026 2023 Syensqo. All rights reserved.

