

NORYL™ RESIN FN150E

REGION EUROPE

DESCRIPTION

NORYL™ FN150E resin is a twin-wall foamable blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS) and offers 20% weight reduction at 6.35mm (0.250") wall. This material contains non-brominated, non-chlorinated flame retardant with a UL94 flame rating of 5VA and V0 at 4mm and has thin-wall impact resistance capability. NORYL FN150E resin exhibits good dimensional stability, low moisture absorption, and improved reliability + productivity. The unique combination of properties allow for designing optimum wall thickness in computer and business machine applications, electrical enclosures/housings, medical equipment, and hospital bed rails and components. In addition, the twin-wall foam offers structural foam at optimal cost efficiency.

GENERAL INFORMATION	
Features	Structural, Flame Retardant, Hydrolytic Stability, Low Warpage, Non-Brominated, Non-Chlorinated, Non-Halogenated, Low Creep Sensitivity, Good Stiffness, Thin Wall
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

TYPICAL PROPERTY VALUES

Revision 20250731

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	40	%	ISO 527
Flexural Stress, yield, 2 mm/min	70	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT			
Gardner Impact (GE)	10 – 20	J	SABIC method
Izod Impact, notched 80*10*4 +23°C	15	kJ/m²	ISO 180/1A
THERMAL			
Thermal Conductivity	0.24	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/120	105	°C	ISO 306
Relative Temp Index, Elec ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	65	°C	UL 746B
PHYSICAL			
Specific Gravity	1.1	-	ASTM D792
Weight Reduction	20	%	SABIC method
Mold Shrinkage on Tensile Bar, flow	0.6 – 0.8	%	SABIC method
Melt Volume Rate, MVR at 280°C/2.16 kg	6	cm³/10 min	ISO 1133
ELECTRICAL			
Relative Permittivity, 1 MHz	2.2	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0047	-	IEC 60250

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dissipation Factor, 1 MHz	0.0039	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.3	-	IEC 60250
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E45329-236752	-	-
UL Recognized, 94-5VA Flame Class Rating	4	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	4	mm	UL 94
Oxygen Index (LOI)	29	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 3	Hrs	
Melt Temperature	260 – 280	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	240 – 260	°C	
Rear - Zone 1 Temperature	220 – 240	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 80	°C	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.