

NORYL™ RESIN GFN2

REGION AMERICAS

DESCRIPTION

NORYL GFN2 resin is a 20% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This general-purpose injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN2 carries a UL746C outdoor suitability rating of F1 and is an excellent candidate for a variety of indoor and outdoor applications including construction, electrical components + displays, lawn and garden equipment. *See NORYL GFN2F resin for FDA food compliant / NSF version.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, IR Transparent, Low Moisture Absorption, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets

TYPICAL PROPERTY VALUES

Revision 20260803

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	90	MPa	ASTM D638
Tensile Strain, Break			
Type I, 5 mm/min	2.6	%	ASTM D638
5 mm/min	2.5	%	ISO 527
Tensile Modulus, 5 mm/min	6200	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D790
Flexural Modulus			
1.3 mm/min, 50 mm span	5800	MPa	ASTM D790
2 mm/min	6540	MPa	ISO 178
Hardness, Rockwell L	106	-	ASTM D785
Tensile Stress, break, 5 mm/min	97	MPa	ISO 527
Tensile Modulus, 1 mm/min	7070	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	167	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, Unnotched			
23°C	650	J/m	ASTM D4812
Izod impact, notched			
80°10°4 +23°C	11	kJ/m²	ISO 180/1A
23°C	119	J/m	ASTM D256

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
-40°C	96	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	22	J	ASTM D3763
Charpy Impact, notched, 23°C	11	kJ/m²	ISO 179/2C
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	143	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
CTE			
-40°C to 90°C, flow	3.3E-05	1/°C	ASTM E831
-40°C to 90°C, xflow	9.0E-05	1/°C	ASTM E831
-40°C to 90°C, flow	3.3E-05	1/°C	ISO 11359-2
-40°C to 90°C, xflow	9.0E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	143	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	143	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	137	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	90	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.2	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.2 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	9	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/5.0 kg	8	cm³/10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Dielectric Strength, in oil, 3.2 mm	16.5	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	2.86	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0008	-	ASTM D150
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥6	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥6	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 4	≥1.5	mm	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D495
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-221161	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
Oxygen Index (LOI)	26	%	ASTM D2863
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.