

Micromax™ 5018G

Electronic Inks & Pastes

PRODUCT DESCRIPTION

UV Curable Dielectric

Polymeric dielectric composition Micromax™ 5018G is a green UV curable, solvent less, screen printable composition used in encapsulant and crossover applications for both rigid and flexible circuit manufacture. It offers the advantages of rapid cure and excellent processing latitude while maintaining excellent electrical and physical properties after cure, including excellent crosshatch adhesion to print-treated and good adhesion to non-print-treated PET substrate and conductor. It is fully compatible with Micromax™ 5000's Series conductor compositions.

Product benefits

- Best insulating UV cure dielectric

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value	Unit
Application	Membrane switch	dielectric
Color	Green	
Odor description ¹	Slight	
Solvent or thinner	Not recommended	
Density	1.28	g/cm ³
Solid content ²	100	%
Maximum Service Temperature ³	70	°C

TECHNICAL DATA

Rheological Properties	Value	Unit
Viscosity ⁴	15 to 30	Pa.s
Application Technique	Value	Unit
Mask mesh	200 to 280	
Theoretical coverage ⁵	290	cm ² /g
Recommended film thickness ⁶	25.4 to 30.48	µm
Mechanical Properties	Value	Unit
Adhesion ⁷	5B	class
Electrical Properties	Value	Unit
Dielectric Constant ⁸	4.4	
Insulation Resistance ⁹	≥1E10	Ohm
Breakdown Voltage ¹⁰	≥500	V
Storage and Stability	Value	Unit
Shelf life ¹¹	6	months

¹Slight, pleasant

²150°C

³on Polyester Film

⁴Brookfield 1/2RVT, 10 rpm #14 spindle, 25°C

⁵at 25.4µm, coating given by 280-mesh stainless steel

⁶after UV cure

⁷The same result, Dielectric to Polyester Scotch Tape #600 and Conductor to Dielectric, ASTM D3359-78.

⁸ASTM D150, at 1 KHz

⁹sq at 25.4µm

¹⁰ASTM D150, V/25.4µm DC

¹¹in unopened containers, from date of shipment, stable environment at room temperature between 5°C - 30°C

PROCESSING GUIDELINES

Substrates

Polyester, polyimide, epoxy glass

Screen types

Polyester, stainless steel

Printing

Semiautomatic and manual

Typical thickness (after cure)

Printed with 200 - 280 mesh stainless steel screen

1 - 1.2 mil

Two prints of dielectric are strongly recommended to achieve maximum circuit reliability.

Work life

> 2 hours

Curing

40 ft/min in air

RPC Industries "QC" Processor Model 1202 AN, with the 200 W/in medium- pressure mercury vapor lamps. Since cure conditions govern characteristics, customers should establish the cure rate required to produce optimum combination of flexibility and hardness.

500 - 1500 mJ/cm

0.500 - 1.500, joules using International Light IL.390B Light Bug or UV Process Supply.

Typical Physical & Electrical Properties on Polyester Film

Test	Properties
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	≥ 1
Flexibility (180° crease over Micromax™ 5007)	No opens
Change in Physical Properties after Environmental Tests*	Insignificant
Change in Insulation Properties after Environmental Tests*	May drop up to one order of magnitude
Coverage (cm ² /g) (Dependent on print thickness) 0.45 mil coating given by 280-mesh polyester	500
Coverage (cm ² /g) (Dependent on print thickness) 0.6 mil coating given by 230-mesh polyester	375
Coverage (cm ² /g) (Dependent on print thickness) 1.1 mil coating given by 200-mesh stainless steel	240

* Environmental Tests

- Thermal Shock (+85°C to -40°C, 30 min. each, 5 cycles)
- Dry Heat (+85°C, 10 days)
- Humidity (+40°C, 95%RH, 10 days) (MIL Std 202E, method 103, cond. A)
- Salt Spray (+35°C, 5% salt, 10 days) (ASTM B117)

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5018G based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature between 5°C - 30°C. Shelf life of material in unopened containers is 6 months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

UV curable compositions such as Micromax™ 5018G should be stored away from heat and light.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom 44.117.4769148	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this

warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.