

Micromax™ 5028B

Electronic Inks & Pastes

PRODUCT DESCRIPTION

Silver Conductor

Micromax™ 5028B silver conductor is used to fabricate low-voltage circuitry, especially on flexible substrates. This composition is particularly suited for applications requiring high conductivity and/or fast curing. It can be used with reel-to-reel, semiautomatic, and manual printers, and offers excellent residence time on the screen.

Product benefits

- Excellent conductivity
- Cadmium, Lead, Nickel and Phthalate free*

*Cadmium, Lead, Nickel and Phthalate 'free' as used herein means that cadmium, lead, nickel, and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value Unit
Application	Membrane switch conductor
Solvent or thinner	Micromax™ 3610
Solid content ¹	69 to 71 %
Maximum Service Temperature ²	110 °C

TECHNICAL DATA

Rheological Properties	Value Unit
Viscosity ³	15 to 30 Pa.s

Application Technique	Value Unit
Mask mesh ⁴	325

Application Technique	Value	Unit
Drying time ⁵	6	min
Drying temperature ⁶	120 to 130	°C
Theoretical coverage ⁷	230 to 320	cm ² /g
Recommended film thickness	8 to 10	µm
Mechanical Properties	Value	Unit
Adhesion ⁸	no material transfer	class
Electrical Properties	Value	Unit
Resistivity ⁹	≤12	mOhm per square
Storage and Stability	Value	Unit
Shelf life ¹⁰	6	months

¹750°C

²on 5-mil Polyester Film

³Brookfield HBT, 10 rpm, #14, 25°C

⁴Screen Types: Stainless steel

⁵box oven

⁶box oven

⁷Dependent on print thickness

⁸3M Scotch Tape #600

⁹at 25µm

¹⁰in unopened containers, from date of shipment, stable environment at room temperature between 5°C - 30°C

PROCESSING GUIDELINES

Substrates

Polyester, paper, epoxy glass

Screen types

Polyester, stainless steel

Printing

Reel-to-reel, semi-automatic, manual

Typical circuit line thickness

Printed with 325-mesh stainless steel screen

8 - 10 µm

Work life

> 1 hours

Clean-up solvent

Ethylene glycol or Diacetate

Drying

Box oven: 120 - 130°C for 6 minutes

Reel-to-reel: 140°C for 1 - 1.5 minutes

Dry and cure in a well-ventilated oven or conveyor dryer where the exhaust meets environmental regulations.

Typical Physical Properties on 5-mil Polyester Film

Test	Properties
Resistivity after Flex (mΩ/sq at 25.4μm) 15 sec after test Crease (180°, 1 cycle)	< 100
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	≥ 2
Soldering	Not Recomm ended
Change in Physical Properties after Environmental Tests*	Insignificant
Change in Electrical Properties after Environmental Tests* (%)	< 10

* Environmental Tests

- Thermal Shock (+85°C to -40°C, 30 min. each, 5 cycles)
- Dry Heat (+85°C, 20 days)
- Humidity (+60°C, 95%RH, 1000 hr) (MIL Std 202E, method 103, cond. A)
- Salt Spray (+35°C, 5% salt, 10 days) (ASTM B117)
- Silver Migration (1 V DC/25.4μm gap, +40°C, 90% RH, 500 hr, tested on 1016μm and 1778μm gaps)
- Sulfate Dioxide (+45°C, 90% RH, 500 hrs in a 9-liter chamber containing 500 mg of sulfur)

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5028B based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature between 5°C - 30°C. Shelf life of material in unopened containers is 6 months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom 44.117.4769148	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.