

Micromax™ 5081R

Electronic Inks & Pastes

PRODUCT DESCRIPTION

Silver Brazing Low Temperature Braze System

Micromax™ 5081R and 5082R constitute a two component, all thick films paste system designed to facilitate the use of high temperature solders and low temperature alloys on :

- 96% alumina and Low temperature cofire ceramic (Micromax™ GreenTape™ 951 low temperature co-fired ceramic system).

- Alumina
- Multilayer hybrid circuits

Product benefits

- High strength, high reliability attachment mechanism
- Hermetic packaging
- Compatibility with thick film resistors, as well as all conventional IC and lid attach processes
- Phthalate and Cadmium free*

* Phthalate and Cadmium oxide 'free' as used herein means that cadmium and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value Unit
Application	LTCC Ag/Pt conductor
Solvent or thinner	Micromax™ 7502R
Blend member or series	5081R and 5082R

TECHNICAL DATA

Rheological Properties	Value Unit
Viscosity ¹	60 to 120 Pa.s

Application Technique	Value	Unit
Mask mesh	325	
Mask emulsion	13	µm
Drying time	10 to 15	min
Drying temperature	150	°C
Recommended film thickness	12 to 15	µm
Leveling time	≥10	min
Electrical Properties	Value	Unit
Resistivity ²	3.5 to 5	mOhm per square
Storage and Stability	Value	Unit
Shelf life ³	6	months

¹Brookfield HBT, UC&SP,, SC4-14/6R, 50 rpm, 25°C ± 0.2°C

²at 10µm fired thickness

³in unopened containers, from date of shipment, stable environment at room temperature between 5°C - 30°C

PROCESSING GUIDELINES

Design & compatibility

Compatibility

Whilst Micromax™ has tested this composition with the materials specified above and the recommended processing conditions, it is impossible or impractical to cover every combination of materials, customer processing conditions and circuit layouts. It is therefore essential that customers thoroughly evaluate the material in their specific situations in order to completely satisfy themselves with the overall quality and suitability of the composition for its intended application (s).

Substrates

Substrates of different compositions and from various manufacturers may result in variations in performance properties.

Screen types

Print onto fired substrate using a 325-mesh stainless steel screen with a 13µm emulsion build up.

Printing

The composition should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean burr-free spatula (flexible plastic or stainless steel) for about 1-2 minutes. Care must be taken to avoid air entrapment. Printing should be performed in a

well-ventilated area.

Note: Optimum printing characteristics are generally achieved in the room temperature range of 20°C - 23°C. It is therefore important that the material, in its container, is at the temperature prior to commencement of printing. Class 10,000 printing area is recommended for building complex hybrids and multilayer circuits, otherwise severe yield losses could occur.

Thinning

Micromax™ 5081R and 5082R compositions are optimized for screen printing and thinning is not normally required. Use the Micromax™ recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non recommended thinner may affect the rheological behavior of the materials and their printing characteristics.

Drying

Allow prints to level for over 10 minutes at room temperature, then dry for ≥ 10 -5 minutes at 150°C.

Dry in a well-ventilated oven or conveyor dryer.


Firing

850°C peak held for 10 minutes on 30 minute cycle in an air atmosphere. Fired thickness of Micromax™ 5081R should be 12-15µm.

Fire in well-ventilated belt, conveyor furnace or static furnace. Air flows and extraction rates should be optimized to ensure that oxidizing conditions exist within the muffle and that no exhaust gases enter the room.

Attachment

Once the substrate has been prepared with Micromax™ 5081R and 5082R, pins, window frames or heat sinks may be attached with braze alloys (Au/Sn), preforms or pastes. Brazing is performed in nitrogen atmosphere using fixed fixtures which position the attachment and braze alloy directly on top of the Micromax™ 5081R/5082R metallization.

FIGURE 1. 30 MINUTES PROFILE

Typical Fired Properties*¹

Test	Properties
PGA Reliability Thermal Cycle* ² (lbs)	≥ 15
PGA Reliability Thermal Aging* ³ (lbs)	≥ 15
Seal Ring Reliability* ⁴ (Atm cm ³ /s)	< 10 ⁻⁸

*1 Average tensile pull strength of a pin in a standard grind array (PGA) brazed on 96% alumina or Micromax™ 951 GreenTape™. PGA consist of 1.8mm diameter pad of Micromax™ 5081R/5082R, and a 400µm diameter Kovar pin with a 800µm diameter nail head. 80Au/20Sn braze preform.

Firing : 30 minute cycles to a peak temperature of 850°C for 10 minutes.

*2 200 cycles, -40°C to 125°C, Rapid transfer

*3 200 hrs in air at 150°C

*4 Helium leak test to Kovar seal ring on Micromax™ 951 GreenTape™, 100 thermal cycles, -25°C to +85°C

All values reported here are results of experiments in our laboratories intended to illustrate product performance potential with a given experimental design. They are not intended to represent the product's specifications, details of which are available upon demand.

General

Performance will depend to a large degree on care exercised in screen printing. Scrupulous care should be taken to keep the composition, printing screens and other tools free of metal contamination. Dust, lint and other particulate matter may also contribute to poor yields.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature between 5°C - 30°C. Shelf life of material in unopened containers is 6 months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom 44.117.4769148	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not

guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.