

Micromax™ 5092D

Electronic Inks & Pastes

PRODUCT DESCRIPTION

PTC Thermistor Composition

Micromax™ 5091D, Micromax™ 5092D and Micromax™ 5093D positive temperature coefficient (PTC) Thermistor compositions are intended for making PTC Thermistor in thick film microcircuits using conventional thick film processing. Potential applications include temperature sensors, temperature compensation elements, and heaters.

Product benefits

- Linear dependence of resistance with temperature
- Compatibility with thick film processing
- Blendability
- High positive TCR
- Laser trim stability
- Environmental stability

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value Unit
Application	Chip resistor
Solvent or thinner	Micromax™ 4553
Blend member or series	5091D/5092D/5093D

TECHNICAL DATA

Rheological Properties	Value Unit
Viscosity ¹	150 to 250 Pa.s

Application Technique	Value	Unit
Mask mesh	200	
Mask emulsion	12 to 18	µm
Drying time	10 to 15	min
Drying temperature	150	°C
Recommended film thickness	23 to 27	µm
Leveling time	5 to 10	min
Electrical Properties	Value	Unit
Resistivity ²	90 to 110	Ohm per square
Hot Temperature Coefficient Resistance ³	2800 to 3200	ppm/°C
Cold Temperature Coefficient Resistance ⁴	2800 to 3200	ppm/°C
Storage and Stability	Value	Unit
Shelf life ⁵	6	months

¹Brookfield HAT, UC&SP, 10 rpm, 25°C

²Terminations Ag/Pd Micromax™ 7484; Substrate 96% alumina; Printing 200-mesh stainless steel screen (15±3 µm emulsion thickness) to a dried thickness 25±2 µm; Firing - recommended short profile to a peak temperature of 850°C for 10 minutes. Resistor geometry for R, laser trim stability: 1.5 x 1.5 mm.

³Resistor geometry for TCR, laser trim stability: 1.5 x 1.5 mm. Measured from +25 to +125°C.

⁴Resistor geometry for TCR, laser trim stability: 1.5 x 1.5 mm. Measured from -55 to +25°C.

⁵in unopened containers, from date of shipment, stable environment at room temperature between 5°C - 30°C

PROCESSING GUIDELINES

Terminations

Reported properties are based on tests with Micromax™ 7484 Ag/Pd conductor composition, prefired at 850°C. Excellent results have also been obtained using Ag Micromax™ 6160, prefired at 850°C.

Substrates

Properties are based on tests on 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variations in performance properties.

Printing

Specified properties are based on resistors printed to 25±2µm dried print thickness. This is readily achieved using 200-mesh stainless steel screens with 15±3µm emulsion thickness.

Drying

Prints should be allowed to level 5-10 minutes at room temperature and then dried 10-15 minutes at 150°C.


Firing

Resistivity and TCR specifications are based on the recommended 30 minutes firing profile with a 10 minute peak at 850°C. Slight variation in resistance and TCR will occur when longer firing profiles or higher peak temperature are used.

Encapsulant

In general, glass encapsulation is not required. However, for applications in need of mechanical protection or protection from extreme environments such as high temperature nitrogen or forming gas, encapsulant Micromax™ 9137, or QQ550 fired at 500°C is recommended.

FIGURE 1. 30 MINUTES PROFILE



Typical PCT Thermistor Properties

Test	Properties
Post Laser Trim Stability*1 (%) 25°C/1000 hours	< 0.2
Post Laser Trim Stability*1 (%) 85%RH/85°C/1000 hours	< 0.2
Post Laser Trim Stability*1 (%) 150°C/1000 hours	< 0.2

*1 This data is based on tests of 1.5 x 1.5mm resistors trimmed to 1.5 x initial value with a single plunge cut. All resistors were un-encapsulated.

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5091D, 5092D & 5093D based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature between 5°C - 30°C. Shelf life of material in unopened containers is 6 months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

44.117.4769148

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.