

Micromax™ 5418

Electronic Inks & Pastes

PRODUCT DESCRIPTION

Platable Termination for Chip Resistor Applications

Specially developed for chip resistors applications, Micromax™ 5418 is a platable lead-free*, cadmium-free* silver palladium C1 termination that meets the needs of a high performance and green product

Product benefits

- Superior sulfur resistance by 18% Pd content
- Freedom to design the desired %Pd by blending with Micromax™ 5421E (0.5%Pd) conductor
- Cadmium, Lead, Nickel and Phthalate free*
- High acid resistance and platable
- Excellent solder leach resistance with lead-free solder
- Compatible with Micromax™ 00X1Z (00X0) and 0FxxA resistor series

*Cadmium, Lead, Nickel and Phthalate 'free' as used herein means that cadmium, lead, nickel, and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value Unit
Application	Resistor termination
Solvent or thinner	Micromax™ 4553
Solid content ¹	75 to 77 %
Fineness Of Grind	≤20 µm
Fineness Of Grind	≤10 µm

TECHNICAL DATA

Rheological Properties	Value Unit
Viscosity ²	220 to 290 Pa.s

Application Technique	Value	Unit
Mask mesh	325	
Mask emulsion	10	µm
Drying time	10 to 15	min
Drying temperature	150	°C
Recommended film thickness	12 to 16	µm
Leveling time	5 to 10	min
Electrical Properties	Value	Unit
Resistivity ³	≤70	mOhm per square
Storage and Stability	Value	Unit
Shelf life ⁴	6	months

¹1050°C

²Brookfield HBT, #14 spindle, UC&S₂, 10 rpm, 25°C

³at 10µm

⁴in unopened containers, from date of shipment, stable environment at room temperature between 5°C - 30°C

PROCESSING GUIDELINES

Substrates

Properties are based on tests using 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variation in performance properties.

Printing

Properties are based on Micromax™ 5418 printed to 14±2µm dried thickness using 325 mesh stainless steel screen with an emulsion thickness of approximately 10µm.

Drying


Allow wet prints to level for 5-10 minutes at room temperature. Dry 10-15 minutes at 150°C.

Firing

Dried prints should be fired in a belt furnace. Use a 30-minutes cycle with a peak temperature of 850°C x 10 minutes.

Micromax™ Standard Profile 850°C x 10 min., 30 min.

(Micromax™ QA Profile)



Properties

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5418 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature between 5°C - 30°C. Shelf life of material in unopened containers is 6 months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom 44.117.4769148	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.