

Micromax™ 5440

Electronic Inks & Pastes

PRODUCT DESCRIPTION

Carbon Conductive Composition

Micromax™ 5440 is a polymer-based, platable carbon paste printable on a variety of substrates. This composition usually will be applied over a fired-on silver that provides sulfur-proof layer for chip components.

Product benefits

- Excellent adhesion on both fired silver and alumina substrates
- Good platability
- Good printability
- Cadmium, Lead, Nickel and Phthalate free*

*Cadmium, Lead, Nickel and Phthalate 'free' as used herein means that cadmium, lead, nickel, and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

PRODUCT INFORMATION

General Properties	Value Unit
Application	Resistor termination
Solvent or thinner	Micromax™ 9245
Solid content ¹	50 %

TECHNICAL DATA

Rheological Properties	Value Unit
Viscosity ²	80 to 120 Pa.s

Application Technique	Value Unit
Mask mesh	200
Mask emulsion	30 to 35 µm

Application Technique	Value	Unit
Drying time	10	min
Drying temperature	150	°C
Recommended film thickness	10 to 15	µm
Leveling time	5	min
Electrical Properties	Value	Unit
Resistivity ³	800	Ohm per square
Storage and Stability	Value	Unit
Shelf life ⁴	3	months

¹150°C

²Brookfield RVT, #14 spindle, UC&S, 10 rpm, 25°C

³at 25.4µm

⁴in unopened containers, from date of shipment, stable environment at refrigerated temperature between 0°C - 5°C

PROCESSING GUIDELINES

Substrates

96% alumina, glass

Printing

10-15µm cured thickness can be achieved using 200 mesh stainless steel screen with an emulsion thickness of 30-35µm.

Drying

Allow wet prints to level for 5 minutes at room temperature. Dry 10 minutes at 150°C in a well-ventilated oven, or belt dryer.

Drying process can be skipped and directly cured depending on the application.

Curing

This composition is best cured at 200°C for 30 minutes. Variation in the curing temperature and/or time at the temperature may result in variation in the final properties.

Plating

Chips terminated with Micromax™ 5440 and processed as recommended can be electroplated in conventional processes.

Properties

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5440 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at refrigerated temperature between 0°C - 5°C. Storage at room temperature is not recommended. Shelf life of material in unopened containers is 3 months from date of shipment. Gradual polymerization and associated viscosity increase, and mechanical separation can be expected over a period of a few months. When refrigerating conditions are used for storage, materials should be allowed to equilibrate to room temperature before opening to prevent pick up of moisture from condensation. After the containers are opened, use and storage conditions and the possible effects of contamination make shelf limits unpredictable.

Storage conditions on the product data sheets are intended to represent long-term material storage recommendations and not a shipping or temperature-at-receipt requirement.

Transportation: Under normal shipping conditions, without temperature control, Micromax™ products are not expected to exhibit a change in quality or fitness for use. Should extraordinary events result in extended transportation periods, Micromax™ recommends customers confirm products remain suitable for the intended application.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

WASTE TREATMENT

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedence.

CONTACT INFORMATION

www.macdermidalpha.com

North America	Europe	Asia
470 Research Drive Wilmington, DE, USA 855.622.7813	Bristol & Bath Science Park Dirac Crescent, Emersons Green, Bristol, BS16 7FR, United Kingdom 44.117.4769148	No. 45 Hsing-Point Road Taoyuan City, 330457 Taiwan 886.3.3773588

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2026 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.